

# OXFORD STONE



## OVERVIEW

<b>SPECIES</b>	EUROPEAN OAK
<b>SURFACE</b>	BAND SAW
<b>FINISH</b>	FUMED/UV OIL
<b>GRADES</b>	PRIME/RUSTIC/NATURE
<b>STYLE</b>	PLANK/HERRINGBONE
<b>CONSTRUCTION</b>	ENGINEERED
<b>BACKING</b>	BALTIC BIRCH WATER RESISTANT PLYWOOD
<b>WEAR LAYER</b>	15 mm ( 5/8" ) – 3,5 mm (0.14 in) 20 mm (3/4" ) – 5,5 mm (0.22 in)
<b>THICKNESS</b>	15 mm, 20mm ( 5/8" , 3/4" )
<b>WIDTHS</b>	PLANKS – 130 mm, 180 mm, 220 mm, 260 mm, 300 mm ( 5 1/8" , 7" , 8 5/8" , 10 1/4" , 12" )
<b>LENGTHS</b>	PLANKS 600 mm – 3000 mm ( 2' – 10' ) PLANKS 600 mm – 2150 mm ( 2' – 7' )
<b>HERRINGBONE DIMENSIONS</b>	130mm x 650 mm, 180 mm x 720 mm ( 5 1/8" x 25 19/32" , 7" x 28 11/32" )
<b>EDGES</b>	V4 or V2 micro

## GRADING CRITERIA

<b>PRIME</b>	Grain is a variation of straight grain and medullary rays on boards. Colour fairly uniform. Flat Sawn. No sap allowed. Occasional healthy pin knots up to max 10mm. No cracks allowed.
<b>NATURE</b>	Grain is straight with natural grain variation allowed. Flat Sawn. No sap allowed. Healthy sound knots allowed up to 45mm. Black knots allowed up to 20mm. No cracks allowed.
<b>RUSTIC</b>	Grain can be straight and wavy. Natural colour variations. Flat Sawn. Kissing sap allowance 1-10%. Sound, healthy knots up to 60-70mm. Knots filled, all knots are small and not open. Black knots up to 30mm. End cracks allowed up to 10cm. Kissing Heart allowed.

**Wood is a natural product. Each piece of wood is unique, therefore there will be variations in colour, quantity of knots and shade**



ZENON Sp. z o.o. company reserves the right to change the specifications.

ZENON Sp. z o.o.  
Ul. Ogrodowa 5  
89-632 Brusy  
POLAND  
+ 48 52 398 23 47  
[enquiries@zenonfloors.com](mailto:enquiries@zenonfloors.com)

