

HAZELNUT




OVERVIEW

| | |
|-------------------------------|--|
| SPECIES | EUROPEAN OAK |
| SURFACE | SMOOTH |
| FINISH | FUMED/UV OIL |
| GRADES | PRIME/RUSTIC/NATURE |
| STYLE | PLANK/HERRINGBONE |
| CONSTRUCTION | ENGINEERED |
| BACKING | BALTIC BIRCH WATER RESISTANT PLYWOOD |
| WEAR LAYER | 15 mm (5/8") – 3,5 mm (0.14 in) 20 mm (3/4") – 5,5 mm (0.22 in) |
| THICKNESS | 15 mm, 20mm (5/8" , 3/4") |
| WIDTHS | PLANKS – 130 mm, 180 mm, 220 mm, 260 mm, 300 mm (5 1/8" , 7" , 8 5/8" , 10 1/4" , 12") |
| LENGTHS | PLANKS 600 mm – 3000 mm (2' – 10') PLANKS 600 mm – 2150 mm (2' – 7') |
| HERRINGBONE DIMENSIONS | 130mm x 650 mm, 180 mm x 720 mm (5 1/8" x 25 19/32" , 7" x 28 11/32") |
| EDGES | V4 or V2 micro |

GRADING CRITERIA

| | |
|---------------|--|
| PRIME | Grain is a variation of straight grain and medullary rays on boards. Colour fairly uniform. Flat Sawn. No sap allowed. Occasional healthy pin knots up to max 10mm. No cracks allowed. |
| NATURE | Grain is straight with natural grain variation allowed. Flat Sawn. No sap allowed. Healthy sound knots allowed up to 45mm. Black knots allowed up to 20mm. No cracks allowed. |
| RUSTIC | Grain can be straight and wavy. Natural colour variations. Flat Sawn. Kissing sap allowance 1-10%. Sound, healthy knots up to 60-70mm. Knots filled, all knots are small and not open. Black knots up to 30mm. End cracks allowed up to 10cm. Kissing Heart allowed. |

Wood is a natural product. Each piece of wood is unique, therefore there will be variations in colour, quantity of knots and shade



ZENON Sp. z o.o. company reserves the right to change the specifications.

ZENON Sp. z o.o.
Ul. Ogrodowa 5
89-632 Brusy
POLAND
+ 48 52 398 23 47
enquiries@zenonfloors.com

